

## AEROSIL® R 974

### Hydrophobic fumed silica

#### Characteristic physico-chemical data

Properties and test methods	Unit	Value
Specific surface area (BET)	m <sup>2</sup> /g	150 - 190
pH value in 4% dispersion		3.7 - 4.7
Loss on drying* 2 hours at 105 °C	%	≤ 0.5
C content	%	0.9 - 1.5
Tamped density* modified	g/l	approx. 50
SiO <sub>2</sub> content based on ignited material	%	≥ 99.8
* ex plant The data represents typical values (no product specification).		

#### Registration (substance or components of substance)

##### AEROSIL® R 974

CAS-No.	68 611-44-9
REACH (Europe)	exempted
TSCA (USA)	registered
DSL (Canada)	registered
AICS (Australia)	registered
ENCS (Japan)	registered
KECI (Korea)	registered
IECS (China)	registered
PICCS (Philippines)	registered

AEROSIL® R 974 is a hydrophobic fumed silica aftertreated with DDS (Dimethyldichlorosilane) based on a hydrophilic fumed silica with a specific surface area of 200 m<sup>2</sup>/g.

### Applications and properties

#### Applications

- Silicone rubber and silicone sealants
- Paints and coatings
- Negative toner
- Adhesives
- Coating polymers
- Cosmetics

#### Properties

- Hydrophobic component for thickening and reinforcement of RTV-1 pack silicone sealants
- Improves shelf-life of silicone sealants
- Water resistant, for thickening and hydrophobising of liquid systems
- Rheology control of (complex) liquid systems
- For use in coatings as anti-settling agent, for pigment stabilization and improvement of corrosion protection
- Improves hydrophobicity and rheology of offset printing inks
- Improvement and maintenance of free flow and anti-caking characteristics of powders
- Due to large surface area improved thickening and thixotropic effect as well as transparency

## Safety and handling

Information concerning the safety of this product is listed in the corresponding Safety Data Sheet, which will be sent with the first delivery or upon updating. Such information is also available from Evonik Industries AG, Product Safety Department, E-MAIL [sds-im@evonik.com](mailto:sds-im@evonik.com) or can be downloaded from our homepage [www.aerosil.com](http://www.aerosil.com). We recommend to read carefully the safety data sheet prior to the use of our product.

## Packaging and storage

AEROSIL® R 974 is supplied in multiple layer 10 kg bags. We recommend to store the product in closed containers under dry conditions and to protect the material from volatile substances. AEROSIL® R 974 should be used within 2 years after production.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

### Customer Service

**Europe/ Middle-East/  
Africa/ Latin America**  
**Evonik Industries AG**  
Business Line Silica  
PB 010-A410  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 12532  
FAX +49 6181 59 712532  
[aerosil@evonik.com](mailto:aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

**North America**  
**Evonik Corporation**  
Business Line Silica  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE +1 800-233-8052  
FAX +1 973-929-8502  
[aerosil@evonik.com](mailto:aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

**Asia (excluding Japan)**  
**Evonik (SEA) Pte. Ltd.**  
Business Line Silica  
3 International Business Park  
Nordic European Centre, #07-18  
Singapore 609927  
PHONE +65 6809-6877  
FAX +65 6809-6677  
[aerosil@evonik.com](mailto:aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

**Japan**  
**NIPPON AEROSIL CO., LTD.**  
Marketing & Sales Division  
P.O. Box 7015  
Shinjuku Monolith 13F  
3-1, Nishi-Shinjuku 2-chrome  
Shinjuku-ku, Tokyo  
163-0913 Japan  
PHONE +81 3 3342-1789  
FAX +81 3 3342-1761  
[infonac@evonik.com](mailto:infonac@evonik.com)  
[www.aerosil.jp](http://www.aerosil.jp)

### Technical Service

**Europe/ Middle-East/  
Africa/ Latin America**  
**Evonik Industries AG**  
Business Line Silica  
HPC 911-221 A  
Rodenbacher Chaussee 4  
63403 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59-3936  
FAX +49 6181 59 4489  
[technical.service.aerosil@evonik.com](mailto:technical.service.aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

**North America**  
**Evonik Corporation**  
Business Line Silica  
2 Turner Place  
Piscataway, NJ 08855-0365  
USA  
PHONE +1 888 SILICAS  
PHONE +1 732 981-5000  
FAX +1 732 981-5275  
[technical.service.aerosil@evonik.com](mailto:technical.service.aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

**Asia (excluding Japan)**  
**Evonik Specialty  
Chemicals (Shanghai) Co.,Ltd**  
Business Line Silica  
55 Chundong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 6119-1065  
FAX +86 21 6119-1075  
[technical.service.aerosil@evonik.com](mailto:technical.service.aerosil@evonik.com)  
[www.aerosil.com](http://www.aerosil.com)

**Japan**  
**NIPPON AEROSIL CO., LTD.**  
Applied Technology Group  
3 Mita-Cho  
Yokkaichi, Mie  
510-0841 Japan  
PHONE +81 59 345-5270  
FAX +81 59 346-4657  
[infonac@evonik.com](mailto:infonac@evonik.com)  
[www.aerosil.jp](http://www.aerosil.jp)